

Serial No. 10/574,556
Filing Date: April 3, 2006

Customer No. 26,289
Attorney's Docket No. 2003JP322

Complete set of claims

**RECEIVED
CENTRAL FAX CENTER
JAN 15 2008**

1(canceled).

2(canceled).

3(canceled).

4(canceled).

5(currently amended). A process for producing a semiconductor device, comprising the steps of: forming an insulating layer and an etching stopper layer on a substrate; removing part of the insulating layer by dry etching; and filling an electrically conductive material into a groove or hole thus formed, wherein said etching stopper layer is formed by curing a composition comprising a silicon-containing polymer, wherein 5% to 100% by mole, based on the total number of moles of silicon contained in the silicon-containing polymer, of silicon is contained in a disilylbenzene structure, further where the silicon-containing polymer has a carbon content of not less than 30% by weight, and further where the etching stopper layer is cured at a temperature in the range of 200°C to 500°C for 30 to 50 minutes.

6(canceled).

7(canceled).

8(canceled).

9(canceled).

Serial No. 10/574,556
Filing Date: April 3, 2006

Customer No. 26,289
Attorney's Docket No. 2003JP322

10(canceled).

11(canceled).

12(canceled).

13(canceled).

14(canceled).


15(canceled).

16(canceled).

17(canceled).

18(canceled).

19(previously presented). The process of claim 5, where the disilylbenzene structure is represented by formula (I),




wherein R¹ to R⁴ each independently are selected from hydrogen, an alkyl group, an alkenyl group, a cycloalkyl group, an aryl group, an aralkyl group, an alkylamino group, and an alkylsilyl group, and Ar represents an aryl group.

Serial No. 10/574,556
Filing Date: April 3, 2006

Customer No. 26,289
Attorney's Docket No. 2003JP322

20(previously presented). The process of claim 5, where the disilylbenzene structure is represented by formula (II),



wherein R¹ to R⁴ each independently are selected from hydrogen, an alkyl group, an alkenyl group, a cycloalkyl group, an aryl group, an aralkyl group, an alkylamino group, and an alkylsilyl group; and R⁵ to R⁸ are independently selected from hydrogen, a C₁ to C₃ alkyl group, a halogen atom, a C₁ to C₃ alkoxide group, and a C₁ to C₃ amino group.